

# Technical data sheet

May 2019

---

## Möller Filter Frame System

---

material: **Polystyrene-Regranulate black**

Characteristics:	material density tested according to ISO R119	1,05	g/cm <sup>3</sup>
	Vicat-softening point		
	A/50 tested according to ISO R306	98	°C
	B/50 tested according to ISO R306	88	°C
	tensile strength tested according to ISO R527	22	Mpa
	breaking elongation tested according to ISO R527	3	%
	elasticity module tested according to ISO R178	2500	Mpa
	fire classification according to DIN 53438-2	F2	

Purity: The material does not contain the following substances:  
Halogen, CFC´s, silicone, non-ferrous metals

Above specification rely on data given to us by our supplier.

M. Mette  
Product manager

Möller GmbH & Co. KG  
Am Kindergarten 1  
59872 Meschede